

# PERMABOND® 922

## Allyl Cyanoacrylate Adhesive



Ref. #: 041509PB922

### TYPICAL APPLICATIONS

Metal to Metal  
Name Plates  
Wire Tacking  
Gaskets

### FEATURES & BENEFITS

- ◆ Fast Setting at Room Temperature
- ◆ Rapid Development of High Strength
- ◆ Ease of use – Single Part, No Mixing
- ◆ Excellent Adhesion to Metal Surfaces
- ◆ Will Bond to Most Materials
- ◆ High Temperature Resistance
- ◆ 100% Reactive, No Solvents
- ◆ Nonflammable

### GENERAL DESCRIPTION

**PERMABOND 922** is the original allyl cyanoacrylate adhesive. It is a single part, moderate viscosity liquid that will cure rapidly at room temperature when pressed into a thin film between parts. **PERMABOND 922** will cure to fixture strength in 10 seconds on most surfaces, and rapidly develops high strength with full cure obtained in 24 hours. The adhesive was specifically designed to meet the high temperature resistance required by certain applications. It provides excellent bond strength to steel, aluminum, and most metal surfaces. The cyanoacrylate will also adhere well to a wide variety of other materials including most plastics and rubbers.

In order to withstand high temperature environments, **PERMABOND 922** was designed with a secondary curing mechanism that is activated at temperatures higher than 150°C (302°F). The procedure to activate this mechanism is as follows:

- 1) Parts are bonded and clamped at room temperature for four hours.
- 2) The clamped parts are then heated at 150°C (302°F) for two hours.
- 3) After the two hours, the bond will be thermally resistant up to 250°C (482°F).

Non-Warranty: The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.

PERMABOND  
14 Robinson Street, Pottstown, PA 19464

Application Assistance: 1-800-640-7599 Customer Service: 1-800-714-0170  
Fax No.: 1-800-334-3219

<http://www.permabond.com>

## CURE RATE

The cure rates of cyanoacrylates are dependent on the substrate used, gap, and relative humidity. The table below shows the set time of various substrates. Cyanoacrylate adhesives have limited gap-filling capability. The speed of cure and the ultimate strength might decrease as the gap increases. The cure speed of cyanoacrylates will depend on the ambient relative humidity; the cure rate generally increases with increasing humidity. The cure rate of cyanoacrylates can be increase by applying activator QFS16. However, the application of the activator might decrease the ultimate strength of the bond.

## PHYSICAL PROPERTIES OF THE UNCURED ADHESIVE

<u>Properties</u> Base Compound Color Viscosity, cP Specific Gravity Flash Point, °C (°F) Flammability Solids, % Shelf Life stored at 2°C-7°C (35°F-45°F), months Gap Fill, in (mm)	Allyl Cyanoacrylate Colorless 1600 1.05 95 (202) Nonflammable 100 12 0.017
--	--

## SPEED OF CURE

<u>SET TIME, seconds</u>	
Steel	10
Full Cure, hours	24

## PHYSICAL PROPERTIES OF THE CURED ADHESIVE

Appearance Operating Temperature, °C (°F) Soluble In	Colorless, Transparent Solid -54 (-65) to 250 (482)* Nitroethane, MEK, Acetone
--	--

\*When the procedure in the general description is followed.

## PERFORMANCE PROPERTIES

<u>Lap Shear Strength on</u> (ASTM D1002)	
Grit blasted Steel, psi (N/mm <sup>2</sup> )	3000 (21)
Aluminum, psi (N/mm <sup>2</sup> )	2500 (17)
Polycarbonate	1000 (7)
ABS	600 (4)
Polystyrene	500 (3.5)
Gum Rubber	300 (2)
Valox	600 (4)

\*Denotes failure of the material before the adhesive bond fails.

## HEAT RESISTANCE

The following tables show the performance of Permabond 922 vs. a regular methyl cyanoacrylate.

### Heat Aging\*

Temperature °C (°F)	<u>Permabond 922</u> Shear Strength psi (N/mm <sup>2</sup> )	<u>Methyl Cyanoacrylate</u> Shear Strength psi (N/mm <sup>2</sup> )
25 (77)	3000	3600
100(212)	3900	250
120 (248)	900	0
150 (302)	1500	0
250 (482)	1700	0
300 (572)	0	0

\* Bonds were aged one week at temperature and then tested at 25°C (ASTM D1002).

### Hot Strength\*

Temperature °C (°F)	<u>Permabond 922</u> Shear Strength psi (N/mm <sup>2</sup> )	<u>Methyl Cyanoacrylate</u> Shear Strength psi (N/mm <sup>2</sup> )
25 (77)	3000	3000
100(212)	3300	2400
150 (302)	650	0
250 (482)	1500	0

\* Bonds were cured at room temperature for 24 hours, heated for two hours at temperature shown, and tested at that temperature (ASTM D1002).

## SURFACE PREPARATION

The surface should be free of gross contamination such as dirt, dust, grease or oil. An alcohol wipe is suitable for cleaning most surfaces. Acetone is recommended for epoxies, polyesters, phenolics, melamine, urea formaldehyde, nylon and polyurethane. Optimum strength is obtained by abrading the surface followed by a solvent wipe to remove any loose particles.

## **APPLICATION**

1. For best results the surface should be properly cleaned.
2. Apply the adhesive sparingly to one surface.
3. Assemble the parts making sure that they are correctly aligned.
4. Apply sufficient pressure to ensure that the adhesive spreads into a thin film.
5. Do not move parts until fixture strength is achieved.
6. When bonding polyethylene, polypropylene, PTFE or silicone, we recommend priming the surfaces with Permabond Polyolefin Primer before using the adhesive.

## **STORAGE & HANDLING**

Cyanoacrylate adhesives are subject to an aging process and have a limited shelf life. The shelf life is one year when stored in a refrigerator. It could be less when stored at ambient environment depending on conditions of temperature and humidity.

A note of caution: Before opening, the containers must be warmed to room temperature; otherwise water might condense into the bottle and cause hardening of the adhesive.

Avoid skin contact. Wear polyethylene gloves and safety glasses. Do not use rubber or cloth gloves. Cyanoacrylates can form strong bonds rapidly to skin. To break the bond, peel and flex the skin carefully. Immersion in soapy water aids in breaking the cyanoacrylate bond. Acetone or nail polish remover may also be used. **If cyanoacrylate should come in contact with the eyes, seek medical attention.**

Cyanoacrylate vapors are lachrymatory and can irritate eyes and mucous membranes. Use these materials with proper ventilation.

## **VAPOR CONTROL RECOMMENDATIONS**

1. Use adequate ventilation. Remove adhesive vapors with suitable exhaust ducting. Since cyanoacrylate vapors are heavier than air, place exhaust intake below work area. Activated charcoal filters using an acidic charcoal have been found effective in removing vapors from effluent air.
2. Avoid use of excess adhesive. Excess adhesive outside of the bond area will increase the level of vapors. Automatic dispensing equipment will prevent excess adhesive.
3. Assemble parts as quickly as possible. Long open times will increase level of vapors.

## **CLEAN UP OF SPILLED LIQUID**

When large quantities of cyanoacrylate adhesives are accidentally spilled, the area should be flooded with water that will cause the liquid cyanoacrylate to cure. The cured material can then be scraped from the surface. **NOTE:** The liquid adhesive should not be wiped up with rags or tissue. The fabric will cause polymerization and large quantities of adhesive will generate heat on cure, causing smoke and strong irritating vapors. **ALWAYS FLOOD WITH EXCESS WATER TO CLEAN UP SPILL CONDITIONS.**

**For additional information consult the Material Safety Data Sheet (MSDS).**

**FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN.**