

Permabond A Surface Activator (A905)

is used in conjunction with Permabond A (anaerobic) adhesives and sealants.

A905 is designed to allow non-metallic surfaces to be bonded/sealed. It also accelerates the cure rate of anaerobics and improves bonding to contaminated surfaces. It will also allow the adhesive to cure in a larger gap.

Physical Properties

Colour	Green
Viscosity	0.55 mPa.s
Flashpoint	-26°C
Boiling Point	63°C
Specific Gravity	0.7
Evaporation Rate	7.7*

*Butyl acetate = 1

Storage and Handling

Storage Temperature	5 to 25°C
Shelf Life Stored in original unopened containers	24 months

Users are reminded that all materials, whether innocuous or not, should be handled in accordance to the principles of good industrial hygiene. Full information can be obtained from the Material Safety Data Sheet.

Directions for use:

- Surfaces should be clean, dry and grease free prior to primer application.
- Permabond A905 should be applied either by wiping (using a clean cloth or brush), spraying or dipping components.
- Allow the A905 to evaporate fully, then apply anaerobic adhesive to male and female parts, then assemble.
- Handling time and cure speed will depend on the substrates and adhesive selected. (Handling time is the time from which the joint is assembled to the time when enough strength has developed for the joint to be handled).
- For maximum bond strength, allow adhesive to cure for 24 hours at 23°C.

Permabond A905 is formulated to minimise attack and maximise performance on certain plastics, however it is recommended that the product is tested for compatibility prior to use in production.

Do not mix Permabond A905 directly with anaerobic adhesives

Kontaktadressen Permabond:

Europe: Tel. +44 (0)1962 711661
UK Helpline: 0800 975 9800
Deutschland: 0800 10 13 177
France: 0805 11 13 88
info.europe@permabond.com

US: Tel. 00 1 732-868-1372
Helpline: 800-640-7599
info.americas@permabond.com
Asia: Tel. 00 886 939 49 3310
info.asia@permabond.com

www.permabond.com

Die hierin enthaltenen Informationen und Empfehlungen beruhen auf unserer technischen Erfahrung und sind nach unserem Wissen und Gewissen richtig. Ihre Genauigkeit kann nicht garantiert und keine Verantwortung für sie übernommen werden. Außerdem darf keine hierin gemachte Behauptung als bindende Verpflichtung oder Gewährleistung betrachtet werden. Vor der Verwendung dieser Produkte sollen Kunden ihre eigenen Prüfungen durchführen, um sicherzustellen, daß das jeweilige Produkt für ihre speziellen Bedürfnisse unter ihren eigenen Betriebsbedingungen geeignet ist.