

Permabond ES569 is a single-part heat cured epoxy adhesive with excellent adhesion to metal surfaces as well as composite materials. The high bond strength of this adhesive allows it to replace mechanical fastening, soldering, brazing or welding. This material requires heat in the range between 150°C and 200°C to cure it. ES569 has been designed to be non-sagging, allowing the product to be used in large gaps and on vertical surfaces.

Physical Properties

Chemical Type	Epoxy
Colour	Black Paste
Viscosity	250,000 - 500,000 mPa.s
Maximum Gap Fill	5mm
Density	1.2
Cure Time*	120°C: 60 minutes 150°C: 45 minutes 180°C: 20 minutes 200°C: 15 minutes

*Actual cure times will depend on the time it takes for the adhesive to reach this temperature - for example, large assemblies or a crowded oven will require longer to reach full cure. Alternative, quicker methods of curing include induction, hotplates, infrared lamps and hot-air guns.

Typical Performance

Shear Strength	ASTM D-1002	27-41 MPa (steel) 17-31 MPa (aluminium) 14-41 MPa (zinc)
Coefficient of Thermal Expansion		45 x 10 ⁻⁶ mm/mm/°C
Shore D Hardness		80
Service Temperature*		-40 to +180°C

*Higher temperatures may be endured for short periods providing the parts are not unduly stressed.

Contact Permabond:

Europe: Tel. +44 (0)1962 711661
UK Helpline: 0800 975 9800
Deutschland: 0800 10 13 177
France: 0805 11 13 88
info.europe@permabond.com

Surface Preparation

Surfaces should be clean, dry and grease-free before applying the adhesive. Permabond Cleaner A is recommended for the degreasing of most surfaces. Some metals such as aluminium, copper and its alloys will benefit from light abrasion with emery cloth (or similar), to remove the oxide layer.

Adhesive Application

- The adhesive should be dispensed from the cartridge via the nozzle supplied (this can be cut to give the appropriate sized bead to cover the bond area).
- Apply the adhesive to one surface and avoid entrapping air.
- Assemble parts applying sufficient pressure to ensure the adhesive spreads to cover the entire bond area.
- Use a jig / clamp to prevent parts moving during cure.
- It is advisable not to disturb the joint until the adhesive is fully cured.

Storage and Handling

Storage Temperature	2 to 7°C
Shelf Life Stored in original unopened containers	6 months

Users are reminded that all materials, whether innocuous or not, should be handled in accordance with the principles of good industrial hygiene. Full information can be obtained from the Material Safety Data Sheet.

www.permabond.com

The information given and the recommendations made herein are based on our experience and are believed to be accurate. No guarantee as to, or responsibility for, their accuracy can be given or accepted, however, and no statement herein is to be treated as a representation or warranty. In every case we urge and recommend that purchasers, before using any product, make their own tests to determine, to their own satisfaction, its suitability for their particular purposes under their own operating conditions.