

PERMABOND®

HM161

Anaerobic Retaining Compound



Ref. # 122309PBHM161

FEATURES & BENEFITS

- High viscosity
- Speeds up production
- Improves alignment
- Strengthens joint
- Simple one-part system
- Excellent shear strength
- Good environmental resistance

GENERAL DESCRIPTION

PERMABOND HM161 is a single component liquid that cures only when in contact with metal parts and oxygen is excluded. The liquid adhesive fills the “air space” between parts and upon cure unitizes and retains the mated parts. Thus it prevents their movement relative to each other, eliminating wear, erosion, and pitting. HM161 cures to a tough crosslinked plastic that will prevent the corrosion of mated parts, and provides excellent environmental and temperature resistance.

PHYSICAL PROPERTIES OF THE UNCURED ADHESIVE

Properties	Methylacrylates
Base Resin	100
Solids, %	Green
Color	2000
Mean Viscosity, cp at 25°C (77°F)	1.09
Specific Gravity	>110 (230)
Flash Point, °C (°F)	12
Shelf Life stored @ or below 27°C (80°F), months*	0.010 (0.25)
Maximum Gap Filling, in (mm)	

*Package sizes greater than one liter, six months.

Non-Warranty: The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.

PERMABOND
14 Robinson Street, Pottstown, PA 19464

Application Assistance: 1-800-640-7599 Customer Service: 1-800-714-0170
Fax No.: 1-800-334-3219

SPEED OF CURE

Typical Fixturing Time	10 minutes
Full Strength	24 hours

Measured on clean M10 steel nuts & bolts.

BEHAVIOR ON DIFFERENT SUBSTRATES

PERMABOND HM161 performs best on clean steel and will also perform well on most metals, including aluminum, stainless steel, brass, and plated materials. It will also give good results on oily parts, but for optimum performance parts should be cleaned before applying the retaining compound. When used on materials that have been treated with anti-rust compounds, the anaerobic adhesive/sealant may not cure. Passive materials will induce a "slow cure" and ultimate strength may also be reduced. Generally metals, which induce a "fast cure", will achieve fixturing strength in approximately 10 minutes.

ACTIVITY OF MATERIALS AND FINISHES

Super Active	Active	Inactive	Passive
brass copper magnesium	iron steel aluminum nickel	anodized aluminum cadmium finishes chrome finishes passivated metals stainless steel titanium zinc	ceramics glass plastics paint finishes

EFFECT OF TEMPERATURE ON CURE SPEED

PERMABOND Anaerobic Retaining Compound is designed to cure at room temperature but the cure can be accelerated by heat if a faster cure is needed. Heating the liquid compound above 120°C (248°F) is not recommended [the compound once cured, has an upper operating limit of 150°C (302°F)] For every 10°C rise in temperature, the rate of cure doubles. Conversely for every 10°C drop in temperature, the rate of cure is reduced by a factor of two.

With an anaerobic retaining compound this process is not possible, because it fills up all irregularities and forms a tough plastic that contacts both parts completely, thereby preventing micro-movements. It seals the inner joint from external and internal chemical attack, thus the durability of the assembly is improved. The surface finish of the substrate will affect the strength of the material. The following table shows this relationship.

Relationship between Strength and Surface Finish

<u>Surface Finish (micro-inches)*</u>	<u>Percent Shear Strength Retained</u>
8	45%
16	50%
32	57%
64	70%
70	100%

* Micro-inches = 1×10^{-6} in.

A machine finish will usually yield a surface roughness of 60 to 80 micro-inches that will typically give optimum strength when using HM161.

APPLICATION & DISPENSING

1. **PERMABOND HM161** For best results, clean all surfaces with a cleaning solvent and allow to dry.
2. If the substrates being used are inactive metals or the cure speed is too slow, then spray the parts with **PERMABOND ASC10** and allow to dry.
3. On slip fitted assemblies, apply adhesive on the leading edge of the pin and on the inside of the collar. Assemble with twisting action.
4. On press fitting assemblies, apply the adhesive on the pin and collar. Assemble using a press.
5. On shrink fitted assemblies, apply the adhesive to the pin, heat the collar to create enough clearance and assemble.
6. Allow the parts to fixture before disturbing them.

STORAGE & HANDLING

Material should be stored in the original container in a cool place away from sparks, flame, excessive heat and sunlight. Handling should be done using plastic gloves and proper eye protection. Skin contact should be avoided. If skin contact occurs, the affected area should be washed thoroughly with soap and water. Eye contact should be treated by thorough washing with water followed by medical attention. Adequate ventilation is necessary to prevent inhalation of vapors. Proper Personal Protective Equipment is always recommended when using chemicals. **For more information, consult the Material Safety Data Sheet.**

PERMABOND HM161 has a shelf life of one year when stored at or below 27°C (80°F). Do not freeze. Product removed from original container might be contaminated during use. Do not return this material to the original container.

UNCURED (LIQUID) ANAEROBIC COMPOUND

Uncured anaerobic products contain reactive chemicals. These chemicals can cause skin irritation on individuals

with sensitive skin. Good housekeeping to keep work areas and tools clean, is usually sufficient to prevent skin irritation. Barrier creams and plastic gloves should be used to ensure worker protection against accidental or chronic exposure.

Atomizing the liquid compound into the air can allow it to be inhaled and thereby expose the lungs to the contact irritation possible on the skin. Spray applications are not recommended.

CURED (SOLID) ANAEROBIC COMPOUND

The cured product is a hard inert plastic, which is safe to handle. The curing reaction reacts all of the liquid adhesive (100%) into the solid plastic. No solvents or other substances are released upon cure as is the case with many other adhesives.

FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN.