

Permabond TA430 is a structural acrylic adhesive designed primarily for bonding metals, ferrites, ceramics and some thermoplastics. This adhesive may be used in a variety of structural bonding applications, due to its versatile performance capabilities. TA430 provides high strength while maintaining excellent flexibility, resulting in tough, durable bonds with outstanding impact and peel resistance. Handling strength is achieved in a few minutes at room temperature by using Permabond Initiator 41.

### Physical Properties

<b>Chemical type</b>	Modified acrylic – solvent free
<b>Colour</b>	Off-white liquid
<b>Viscosity</b>	30,000 mPa.s
<b>Density</b>	1.1
<b>Ratio of use</b>	10:1.5 approximately


### Typical Performance

<b>Cure Speed</b>	Gap <sup>†</sup> : ~0mm 0.25mm 0.5mm	<2 minutes 10 minutes 20 minutes
<b>Gap fill</b>		Up to 0.5mm
<b>Fixture time</b>		50-90 seconds
<b>Working strength</b>		30-60 minutes
<b>Full strength</b>	DIN 53283	24 hours
<b>Shear strength</b>	ASTM D-1002	25 MPa (steel)
<b>Peel strength</b>	ISO4578	65 N/25mm
<b>Tensile strength</b>	DIN 53288	25 MPa
<b>Impact strength</b>	ASTM D-950	25 Nmm/mm <sup>2</sup>
<b>Coefficient of thermal expansion</b>	ASTM D-696	80 x 10 <sup>-6</sup> 1/K
<b>Thermal conductivity</b>	ASTM C-177	0.1 W/m <sup>2</sup> K
<b>Dielectric constant</b>	ASTM D-150	4.6 Mhz
<b>Dielectric strength</b>	ASTM D-149	30-50 KVmm
<b>Volume resistivity</b>	ASTM D-257	2 x 10 <sup>13</sup> Ohm.cm
<b>Service temperature*</b>		-50 to +120°C

<sup>†</sup>This information should be used as a guide only, since values obtained depend on the specific nature of the surfaces involved.


\*Higher temperatures may be endured for short periods, providing the parts are not unduly stressed.

### Temperature Durability



All values were generated on "as-received" steel lap shears, as described in ASTM D-1002. Adhesive was cured at room temperature for 48 hours prior to environmental exposure. Test pieces were assembled with no induced gap and subjected to continuous exposure for 1000 hours before testing at room temperature.

### Chemical Resistance



Specimens were immersed for 30 days at 85°C and tested at room temperature.

**This product is not recommended for use in contact with strong oxidizing materials.**

Where aqueous washing systems are used to clean the surfaces before bonding, these aqueous washes can affect the cure and performance of the adhesive. This product may affect some thermoplastics and users must check compatibility of the product with such substrates.

## Surface Preparation

Surfaces should be clean, dry and grease-free before applying the adhesive. Permabond Cleaner A is recommended for the degreasing of most surfaces. Some metals such as aluminium, copper and its alloys will benefit from light abrasion with emery cloth (or similar), to remove the oxide layer.

## Adhesive Application

- Surfaces must be clean, dry and grease-free prior to bonding.
- Apply Initiator 41 to one surface.
- Apply adhesive to the other surface.
- Assemble the components using sufficient force to spread the adhesive thinly. Parts should be bonded immediately and within a maximum of two hours of applying the Initiator.
- Maintain pressure until handling strength is achieved. The time required will vary according to the joint design and surfaces being bonded.
- Allow 24 hours for adhesive to fully cure. Accelerated cure times may be achieved by heating.

## Storage and Handling

<b>Storage Temperature</b>	5 to 25°C
<b>Shelf Life</b> Stored in original unopened containers	12 months

Users are reminded that all materials, whether innocuous or not, should be handled in accordance with the principles of good industrial hygiene. Full information can be obtained from the Material Safety Data Sheet.

## Other Products Available

### Anaerobics

- Toughened
- Gas & water approved
- High temperature resistance
- Flexible

### Cyanoacrylates

- Low bloom / low odour
- Flexible
- High temperature resistance

### Epoxies

- Fast cure
- Toughened
- Flexible grades

### Toughened Acrylics

- Rapid cure
- Low odour

### UV Light Cured

- Glass / plastic bonding
- Optically clear
- Non-yellowing

Contact Permabond:

**Europe:** Tel. +44 (0)1962 711661  
UK Helpline: 0800 975 9800  
Deutschland: 0800 10 13 177  
France: 0805 11 13 88  
info.europe@permabond.com

**US:** Tel. 00 1 732-868-1372  
Helpline: 800-640-7599  
info.americas@permabond.com  
**Asia:** Tel. 00 886 939 49 3310  
info.asia@permabond.com

[www.permabond.com](http://www.permabond.com)

The information given and the recommendations made herein are based on our experience and are believed to be accurate. No guarantee as to, or responsibility for, their accuracy can be given or accepted, however, and no statement herein is to be treated as a representation or warranty. In every case we urge and recommend that purchasers, before using any product, make their own tests to determine, to their own satisfaction, its suitability for their particular purposes under their own operating conditions.